Amendments to the Claims:

This listing of claims will replace all prior versions, and listings, of claims in the application.

Listing of Claims:

Claim 1 (currently amended). A process of providing permanently distressed texture to a nonwoven fabric comprising the steps of:

- a. providing a precursor fibrous nonwoven web, wherein said precursor web is comprised of a blend of: synthetic fibers, selected from the group consisting of polyamide, polyesters, polyolefins, and combinations thereof; and natural fibers consisting of cotton, wood pulp, rayon, lyocell, and combinations thereof;
 - b. providing a three-dimensional image transfer device;
- c. hydroentangling said precursor web on said image transfer device to form a patterned and imaged nonwoven fabric;
- d. laundering said formed patterned and imaged nonwoven fabric to cause slippage between the fibers of the fabric;
- e. said patterned and imaged nonwoven fabric taking on a distressed or wrinkled appearance by virtue of said slippage between fibers of said fabric; and
- f. forming said nonwoven fabric into a roll subsequent to said laundering step.

Application No. 10/045,247 Amendment dated October 7, 2004 Reply to Office Action of July 7, 2004

wherein increasing the level of hydroentangling during said hydroentangling steps acts to diminish the slippage between fibers of the fabric during said laundering step.

Claim 2 (canceled).

Claim 3 (canceled).

Claim 4 (previously presented). A process of making a permanently distressed textured nonwoven fabric as in claim 1, wherein said synthetic fiber is polyester.

Claim 5 (canceled).

Claim 6 (original). A process of making a permanently distressed textured nonwoven fabric as in claim 1, wherein said nonwoven fabric is suitable for use in the apparel industry as a bottom weight or in the home fashions industry as a window covering, bed covering, or furniture cover.

Claim 7 (canceled).

Claim 8 (previously presented). A bottom weight garment comprising an imaged nonwoven fabric formed in accordance with the process of claim 1, said bottom weight garment having a jet dyed finish and a distressed appearance upon laundering, said bottom weight garment having a basis weight of 3.0-8.0 ounces per square yard and a fiber composition of cotton and polyester.

Claim 9 (previously amended). A home fashion articles comprising an imaged nonwoven fabric formed in accordance with the process of claim 1, said home fashion

Application No. 10/045,247 Amendment dated October 7, 2004 Reply to Office Action of July 7, 2004

article having a jet dyed and/or printed finish as well as distressed appearance upon laundering, said home fashion article having a basis weight of 1.0-3.0 ounces per square yard and a fiber composition of polyester and lyocell or rayon fibers.